




PO Box 31126
Dayton, OH 45437
Tel: 937.252.2989 Fax: 937.258.3937
E-mail: info@exciton.com
www.exciton.com

ABS 556: Visible Narrow Band Absorber

Properties

Composition	Proprietary Coordination Complex ¹
Peak Wavelength	556 ± 1 nm (methylene chloride)
Strength	35 L/gm-cm (methylene chloride)
Appearance	Red powder
Solubility	75 gm/L (chloroform), 32.8 gm/L (methylene chloride), 12.1 gm/L (cyclohexanone), 14.3 gm/L (toluene), 5.5 gm/L (methyl ethyl ketone), 1.73 gm/L (hexane)
Melting Point	> 300 °C
Solar Stability	Excellent, loss of only 0.02 OD in 200 hours, 1 sun

Spectrum (methylene chloride)



1. This product is offered by Exciton, Inc. under non-analysis and may be available for licensing for specific applications that require selective absorption and high temperature stability. Please contact Exciton for licensing or additional technical information.

The information presented above is believed to be accurate but is not a specification. The customer is fully responsible for determining the suitability of this product for use in their application. Exciton, Inc. does not represent that the information is sufficient or complete for any specific application.