




PO Box 31126
Dayton, OH 45437
Tel: 937.252.2989 Fax: 937.258.3937
E-mail: info@exciton.com
www.exciton.com

IRA 764: Infrared Absorber

Properties

Composition	Proprietary Dye ¹
Peak Wavelength	764 ± 2 nm (methylene chloride); 771 ± 2 nm (polycarbonate)
Strength	170 L/gm-cm (methylene chloride)
Appearance	Blue-green powder
Solubility	3.5 gm/L (methylene chloride), 8.4 gm/L (chloroform), 0.5 gm/L (toluene), 2 gm/L (acetone),
Melting Point	> 300 °C
Solar Stability	Excellent, loss of only 0.02 OD in 200 hr simulated sunlight

Spectrum (polycarbonate)



1. This product is offered by Exciton, Inc. under non-analysis and may be available for licensing for specific applications that require selective absorption and high temperature stability. Please contact Exciton for licensing or additional technical information.

The information presented above is believed to be accurate but is not a specification. The customer is fully responsible for determining the suitability of this product for use in their application. Exciton, Inc. does not represent that the information is sufficient or complete for any specific application.