




PO Box 31126
Dayton, OH 45437
Tel: 937.252.2989 Fax: 937.258.3937
E-mail: info@exciton.com
www.exciton.com

IRA 980BT: Infrared Absorber

Properties

Composition	Proprietary Organic Salt ¹
Peak Wavelength	986 ± 1 nm (methylene chloride)
Strength	42.8 L/gm-cm (methylene chloride)
Appearance	Green glassy powder
Solubility	Very high solubility in solvents other than water, short chain alcohols
Melting Point	~ 60 °C
Solar Stability	Good

Spectrum (methylene chloride)



1. This product is offered by Exciton, Inc. under non-analysis and may be available for licensing for specific applications that require selective absorption and high temperature stability. Please contact Exciton for licensing or additional technical information.

The information presented above is believed to be accurate but is not a specification. The customer is fully responsible for determining the suitability of this product for use in their application. Exciton, Inc. does not represent that the information is sufficient or complete for any specific application.